


DEPOTAL ANNELÉ®



APPLICATIONS



Le tuyau DEPOTAL® Annelé est conçu pour le transfert de tous types de produits alimentaires, même à température élevée (lait, bière, eau potable, vin, jus de fruits, alcool...).

Attention : Le DEPOTAL® n'est pas conseillé pour le transfert de certains produits gras. Pour ces produits, utiliser notre tuyau NITRIFOOD®.

COMPOSITION



- Tube : EPDM blanc de qualité alimentaire.
- Renfort : trame textile et spires acier galvanisé noyées dans la paroi.
- Revêtement extérieur : EPDM bleu.

POSSIBILITÉS D'ASSEMBLAGE



NRS®

Montage coquille
(Nous consulter)



CARACTÉRISTIQUES



Tuyau robuste résistant à l'usure et aux frottements sur les sols.

Tuyau stérilisable en place par les principaux produits CIP. Tenue au vide et en pression.



+120°C (+160°C en pointe)
-30°C

NORMES



FDA 21 CFR 177.2600, BfR, Règlement (CE) 1935/2004, sans phtalate.



Référence	DN		Ø int		Ø ext		Pression de service		Pression d'éclatement		Rayon de courbure				Vide		Poids	
											Statique		Dynamique					
	mm	inch	mm	inch	mm	inch	bar	PSI	bar	PSI	mm	inch	mm	inch	bar	PSI	kg/m	lb/f
45945125	25	1"	25	0,98	37	1,46	10	145	30	435	50	1,97	70	2,76	-0,9	-13	0,80	0,54
45945132	32	1"1/4	32	1,26	44	1,73	10	145	30	435	60	2,36	80	3,15	-0,9	-13	0,96	0,65
45945138	38	1"1/2	38	1,50	51	2,01	10	145	30	435	70	2,76	120	4,72	-0,9	-13	1,27	0,85
45945151	51	2"	51	2,01	65	2,56	10	145	30	435	90	3,54	150	5,91	-0,9	-13	1,85	1,24
45945163	63	2"1/2	63,5	2,50	79	3,11	10	145	30	435	170	6,69	250	9,84	-0,9	-13	2,49	1,67
45945176	76	3"	76	2,99	90	3,54	10	145	30	435	200	7,87	350	13,78	-0,8	-11,6	2,72	1,83
459451102	100	4"	102	4,02	119	4,69	10	145	30	435	300	11,81	500	19,69	-0,8	-11,6	4,25	2,86
459451125	125	5"	125	4,92	143	5,63	6	87	18	261	625	24,61	895	35,24	-0,8	-11,6	5,7	3,83
459451152	150	6"	152	5,98	172	6,77	4	58	12	174	750	29,53	1075	42,32	-0,8	-11,6	7,94	5,34


Les valeurs ci-dessus sont données pour une utilisation à température ambiante (+/- 20°C) et peuvent varier en fonction des conditions d'utilisation.
Tolérances dimensionnelles : nous consulter.

FAN.0026.09.07/24

Document non contractuel pouvant être modifié sans préavis



DEPOTAL ANNELE®



APPLICATIONS



The DEPOTAL Annelé® hose is designed for the transfer of all types of food products, even at high temperatures (milk, beer, drinking water, wine, fruit juices, alcohol, etc.).

N.B. DEPOTAL® is not recommended for the transfer of certain fatty products. For these products, rather use the NITRIFOOD® hose.

CHARACTERISTICS



Robust hose, resistant to wear and rubbing on the ground.

The hose can be sterilised using the main CIP products. Resistance to vacuum and pressure.



+120°C (+160°C peak)
-30°C

COMPOSITION



- Tube: Food quality white EPDM.
- Reinforcement: textile weft and galvanised steel embedded in the wall.
- External covering: blue EPDM.

STANDARDS



FDA 21 CFR 177.2600, BfR, Regulation (EC) 1935/2004, phthalate free.



ASSEMBLY POSSIBILITIES



Reusable ferrule assembly
(Contact us)

NRS®



Reference	DN		Ø int		Ø ext		Working pressure		Bursting pressure		Bend radius				Vacuum		Weight	
											Static		Dynamic					
	mm	inch	mm	inch	mm	inch	bar	PSI	bar	PSI	mm	inch	mm	inch	bar	PSI	kg/m	lb/f
45945125	25	1"	25	0,98	37	1,46	10	145	30	435	50	1,97	70	2,76	-0,9	-13	0,80	0,54
45945132	32	1 1/4"	32	1,26	44	1,73	10	145	30	435	60	2,36	80	3,15	-0,9	-13	0,96	0,65
45945138	38	1 1/2"	38	1,50	51	2,01	10	145	30	435	70	2,76	120	4,72	-0,9	-13	1,27	0,85
45945151	51	2"	51	2,01	65	2,56	10	145	30	435	90	3,54	150	5,91	-0,9	-13	1,85	1,24
45945163	63	2 1/2"	63,5	2,50	79	3,11	10	145	30	435	170	6,69	250	9,84	-0,9	-13	2,49	1,67
45945176	76	3"	76	2,99	90	3,54	10	145	30	435	200	7,87	350	13,78	-0,8	-11,6	2,72	1,83
459451102	100	4"	102	4,02	119	4,69	10	145	30	435	300	11,81	500	19,69	-0,8	-11,6	4,25	2,86
459451125	125	5"	125	4,92	143	5,63	6	87	18	261	625	24,61	895	35,24	-0,8	-11,6	5,7	3,83
459451152	150	6"	152	5,98	172	6,77	4	58	12	174	750	29,53	1075	42,32	-0,8	-11,6	7,94	5,34

Values below are given for use at ambient temperature (+/- 20°C)
and may vary depending upon conditions of use.
Dimensional tolerances: contact us.

FAN.0026.09.07/24

Non-contractual document subject to change without notice.